

## Torlon® 4301

### polyamide-imide

Torlon 4301 is a wear-resistant grade of polyamide-imide (PAI) resin. It has a good balance of mechanical properties and wear resistance. It offers high flexural and compressive strength with a low coefficient of friction and outstanding wear resistance at both high velocity and high pressure conditions.

Torlon PAI has the highest strength and stiffness of any thermoplastic up to 275°C (525°F). It has outstanding resistance to wear, creep, and chemicals.

Potential applications for Torlon 4301 polyamide-imide include thrust washers, spline liners, valve seats, bushings, bearings,

wear rings, cams and other applications requiring strength at high temperature and resistance to wear.

Injection Molding Grades:

- High Flow: Torlon 4301 HF
- Low Flow: Torlon 4301 LF
- Low Flow Small Pellets: Torlon 4301 LFSP

Extrusion Grades:

- High Flow: Torlon 4301-EXT
- Higher Flow: Torlon 4301-HQ

#### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Additive	• PTFE + Graphite Lubricant		
Features	• Flame Retardant • Good Chemical Resistance • Good Creep Resistance	• Good Wear Resistance • High Heat Resistance • High Temperature Strength	• Low Friction • Self Lubricating • Semi Conductive
Uses	• Aerospace Applications • Aircraft Applications • Automotive Applications • Bearings • Bushings • Cams	• Gears • Industrial Applications • Industrial Parts • Machine/Mechanical Parts • Metal Replacement • Oil/Gas Applications	• Rollers • Sealing Devices • Seals • Thrust Washer • Transmission Applications • Washer
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• BOSCH N28 BN05-OX2 N28 BN05-OX2, BN0512-CDSX-0Cgr01SO <sup>1</sup>		
Forms	• Pellets		
Processing Method	• Injection Molding	• Machining	• Profile Extrusion

#### Physical

	Typical Value	Unit	Test Method
Specific Gravity	1.46	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.35 to 0.60	%	ASTM D955
Water Absorption (24 hr)	0.28	%	ASTM D570

#### Mechanical

	Typical Value	Unit	Test Method
Tensile Modulus			
-- <sup>2</sup>	6550	MPa	ASTM D1708
--	6830	MPa	ASTM D638
Tensile Strength	113	MPa	ASTM D638
Tensile Stress <sup>3</sup>	163	MPa	ASTM D1708

Mechanical	Typical Value	Unit	Test Method
Tensile Elongation			
Break <sup>2</sup>	7.0	%	ASTM D1708
Break	3.3	%	ASTM D638
Flexural Modulus			ASTM D790
23°C	6890	MPa	
232°C	4960	MPa	
Flexural Strength			ASTM D790
23°C	215	MPa	
232°C	112	MPa	
Compressive Modulus	5310	MPa	ASTM D695
Compressive Strength	166	MPa	ASTM D695
Coefficient of Friction			ASTM D3702
-- <sup>4</sup>	0.18		
-- <sup>5</sup>	0.030		
-- <sup>6</sup>	0.31		
-- <sup>7</sup>	0.39		
Wear Factor			ASTM D3702
Dry: 0.25 m/s, 3.4 MPa (50 fpm, 500 psi)	14.0	in <sup>3</sup> ·min <sup>-1</sup> / 10/ft·lb·hr	
Dry: 4 m/s, 0.2 MPa (800 fpm, 31.25 psi)	17.0	in <sup>3</sup> ·min <sup>-1</sup> / 10/ft·lb·hr	
Lubricated: 0.25 m/s, 6.9 MPa (75 fpm, 1000 psi)	9.00	in <sup>3</sup> ·min <sup>-1</sup> / 10/ft·lb·hr	
Lubricated: 4 m/s, 5.2 MPa (800 fpm, 750 psi)	0.400	in <sup>3</sup> ·min <sup>-1</sup> / 10/ft·lb·hr	
Impact	Typical Value	Unit	Test Method
Notched Izod Impact	64	J/m	ASTM D256
Unnotched Izod Impact	410	J/m	ASTM D256
Thermal	Typical Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	279	°C	
Thermal Conductivity	0.53	W/m/K	ASTM C177
Coefficient of Linear Thermal Expansion	0.000025	cm/cm/°C	ASTM D696
Electrical	Typical Value	Unit	Test Method
Surface Resistivity	8.0E+17	ohm	ASTM D257
Volume Resistivity	8.0E+15	ohm·cm	ASTM D257
Injection	Typical Value	Unit	
Drying Temperature	177	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	304	°C	
Nozzle Temperature	371	°C	
Mold Temperature	199 to 216	°C	
Back Pressure	6.89	MPa	
Screw Speed	50 to 100	rpm	
Screw L/D Ratio	18.0:1.0 to 24.0:1.0		

---

**Injection Notes**

---

Minimum drying conditions: 3 hours at 350°F (177°C), 4 hours at 300°F (149°C), or 16 hours at 250°F (121°C).

Compression Ratio: 1:1 to 1.5:1

Begin hold pressure at a high setting 6,000-8,000 psi (41.37-55.16 MPa), for several seconds, then drop off to 3,000-5,000 psi (20.69-34.48 MPa), for the duration of the hold pressure sequence.

Molded parts must be post cured.

**Notes**

Typical properties: these are not to be construed as specifications.

---

<sup>1</sup> Material should be Tempered (Cured).

---

<sup>2</sup> ASTM Test Method D1708 has been used to measure the tensile properties of PAI and similar materials because the small test specimen conserved material.

Today the most widely used specimen is the Type 1 bar of ASTM D638. These D1708 values are included for historical purposes and they should not be compared to the D638 values.

---

<sup>3</sup> ASTM Test Method D1708 has been used to measure the tensile properties of PAI and similar materials because the small test specimen conserved material. Today the most widely used specimen is the Type 1 bar of ASTM D638. These D1708 values are included for historical purposes and they should not be compared to the D638 values.

---

<sup>4</sup> Lubricated: 0.25 m/s, 6.9 MPa (75 fpm, 1000 psi)

---

<sup>5</sup> Lubricated: 4 m/s, 5.2 MPa (800 fpm, 750 psi)

---

<sup>6</sup> Dry: 0.25 m/s, 3.4 MPa (50 fpm, 500 psi)

---

<sup>7</sup> Dry: 4 m/s, 0.2 MPa, (800 fpm, 31.25 psi)

[www.SolvaySpecialtyPolymers.com](http://www.SolvaySpecialtyPolymers.com)

## Contact Solvay Specialty Polymers

Europe, Middle East and Africa [SpecialtyPolymers.EMEA@solvay.com](mailto:SpecialtyPolymers.EMEA@solvay.com)

Americas [SpecialtyPolymers.Americas@solvay.com](mailto:SpecialtyPolymers.Americas@solvay.com)

Asia and Australia [SpecialtyPolymers.Asia@solvay.com](mailto:SpecialtyPolymers.Asia@solvay.com)

## In Case of Accident

Europe & South America +44(0).1235.239.670 (CareChem 24)

North America +1.703.527.3887 (Chemtrec)  
+1.800.424.9300 (Toll Free Chemtrec)

China & Taiwan +86.10.5100.3039 (CareChem 24)

East/South East Asia +65.3158.1074 (CareChem 24)

## Product Information, Technical Assistance and MSDS

Europe +39.02.3835.1

Americas +1.770.772.8760  
+1.800.621.4557

Japan +81.3.5425.4300

China & South East Asia +86.21.5080.5080

Material Safety Data Sheets (MSDS) are available by emailing us or contacting your sales representative. Always consult the appropriate MSDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.  
© 2012 Solvay Specialty Polymers. All rights reserved.

